Nasaco International Limited

Petite Rue 3, 1304 Cossonay, Switzerland
Tel: + 41 21 863 0310 Fax: + 41 21 863 0311 email: info@nasaco.ch

PRODUCT DATA SHEET

NASFROTH 102

Nasfroth 102 flotation frother is a formulated mixture of propylene glycol methyl and normal butyl ethers. It is the high molecular weight product in the Nasfroth range of frothers, as such it is a broad band frother with good selectivity. Nasfroth 102 is recommended in situations where a high degree of selectivity is required together with high recovery particularly of coarse particles; being a stronger frother it is recommended for a broad range of particle flotation from medium to coarse particles. Although most commonly used in alkaline flotation, Nasfroth 102 is being used in both acid and alkaline flotation systems from pH 3.5 to pH 12.3

Nasfroth 350 is slightly soluble in water. The product is stable under normal storage conditions.

PHYSICAL PROPERTIES

Flash Point	130°C	(PMCC)
Appearance	Brown liquid	
Odour	Slight	
Specific Gravity	1.08	(25/25°C)
Water Solubility	<5g/100g	
Freezing Point	-20°C	
Boiling Point	>200°C	

Safety and Handling

Nasaco International Limited encourages its customers to use their products in ways which promote safe handling and good industrial practise. Before handling this product, ALWAYS carefully read and understand the instructions and hazard warnings on the container label. Further information may be obtained from the Safety Data Sheet for Nasfroth 102.

Normal safe handling will not result in health or industrial hygiene hazard. If Nasfroth102 comes into contact with the eye it may cause moderate eye irritation and corneal injury. The following guidelines should be followed:

- Wear Chemical Workers goggles, clean body covering clothing and rubber gloves when handling Nasfroth 102
- Contaminated clothing should be thoroughly washed before re-use
- If eye contact occurs the eyes should be flushed with water for 15 minutes and medical advice sought.

Application

The three variables in the application of Nasfroth 102 are dosage, point of addition and frequency of addition.

Dosage rates of frother vary from operation to operation, they are largely dependent of ore type, grind size and water chemistry. Whilst dosages vary from 5 to 50 g/t, normal rates are from 15 - 30g/t.

Because of the hydrophobic nature of Nasfroth 102, the addition of the frother at the head of the flotation circuit with short conditioning is normally sufficient for most operations. In some cases, stage addition of frother can lead to improved economics by reducing overall frother dosage, often addition at the head of the roughers and in the scavengers is sufficient. Testwork will define the optimum.

The chemical nature of Nasfroth 102 means that is best suited to operations with a medium to coarse particle size in flotation. It is a selective frother and will tend to give improved concentrate grades.

Protective Clothing

Personnel handling chemicals should wear clean body covering clothing, gloves and chemical workers goggles.

Contamination incidental to normal handling is unlikely to occur, if however skin or eye contact does occur, the following first aid guidelines should be followed.

First Aid

Skin - If skin contact occurs, wash the effected area with plenty of water and a neutral soap for a minimum of five minutes.

Eye - If eye contact occurs, wash with plenty of clean water for a minimum of fifteen minutes, holding the eye open. Medical advice should be sought.

Ingestion - In the case of ingestion, induce vomiting and immediately seek medical attention.

Storage and Handling

Recommended materials of construction for storage and distribution systems of Nasfroth 102 include: Black iron, mild and stainless steel, brass and copper. Nasfroth 102 has a shelf life of at least three years, the low freezing point allows outside storage - out of direct sunlight.
Extensive evaluation has shown that Nasfroth frothers are compatible with various types of distribution systems.

Toxicity and Environmental Impact

Nasfroth frothers exist at low concentrations in flotation cells. A majority of the frother is present in the concentrate and is incinerated in smelting operations. The remainder is usually transferred to the tailings pond or recycled.

The LC_{50} for Daphnia is > 10,000 mg/l. The product is regarded as Practically non-toxic.

The recommended method of disposal is by burning under controlled conditions.
Customers are advised to check with local, state or national legislation governing disposal of waste material.

Fire

In the case of fire, types A and B extinguishers should be used.

Packaging and Shipping

Nasfroth 102 is packed in 212 liter mild steel drums, IBC containers or bulk containers of 23000 liters. Net and gross weights are:

Drum net weight:	195kg
Drum gross weight:	213kg
IBC net weight:	940kg
IBC gross weight:	980kg

Nasfroth 102 is classified according to the Commission of the European Communities (Directive 1272/2008) as Category 1A can cause serious damage to eyes

Notice
Although the information contained herein is presented in good faith and is to the best of Nasaco International Limited's knowledge true and accurate, it is made for informal purposes only and without any warranty whatsoever. Due to the special nature of the product and its applications, Nasaco International Limited does not accept any responsibility or liability whatsoever which may result from the use of this information. The information contained herein is not to be construed as a license to operate under, or a recommendation to infringe any existing patents, nor should it be confused with any Governmental or insurance requirements or with any national or international safety codes.